


DashCrete

Splatter Dash Coat



DESCRIPTION • *DashCrete – Splatter Dash Coat* is a single component, fiber reinforced cement-based, polymer-modified dash coat with excellent bonding properties. It is used as the first coat in two or three coat plastering systems.

USES • *DashCrete* is suitable for use in interior and exterior vertical applications as base coat applied over masonry, concrete, block and brick. It is used to promote mechanical bond between it and the brown coat or colored plaster, which is applied later. It acts as a bonding agent between the substrate and the next subsequent layers. *DashCrete* can also be applied on metal lath including paper backed lath. It is placed into the lathe to form the plaster “keys” to hold it in place.

ADVANTAGES

- ✓ Excellent bonding properties.
- ✓ Can be applied to non-flat surfaces.
- ✓ Excellent waterproofing properties.
- ✓ Single component, easy to use and apply.
- ✓ Highly flexible.
- ✓ Builds thickness and strength.
- ✓ Increases opacity of finish coat.
- ✓ Provides substrate integrity for latter coats.

COVERAGE • Coverage depends on the tools used for application, surface irregularities and roughness. Coverage is approximately 10-12 sq meters per 35 kg bag at a 3 mm average thickness.

LIMITATIONS • Do not mix or apply if ambient temperature is expected to drop below 5°C during installation or in the proceeding 24 hours, or if rain is expected in the proceeding 24 hour period after application. Do not mix or apply when ambient temperature is expected to exceed 35°C. Avoid working in direct sunlight. Temporary protection from weather and other damage must be provided at all times until entire job is completed.

SURFACE Preparation • *DashCrete* can be applied on an array of bases. It is very compatible with concrete masonry and new concrete. All bases should be sufficiently rigid, clean of any surface contamination that may prevent good suction. Dense, smooth surfaces, and those retaining excessive amount of form release agent, can cause delamination from the base. High gloss, or low absorption surfaces can be made more receptive by sandblasting. Any painted or coated surfaces should be sand blasted or pressure

washed to remove existing coating. Under extreme weather conditions and on highly porous, absorptive surface, the substrate must be sufficiently moistened.

MIXING • Mixing should be completed by mechanical methods, preferably with a paddle type mixer. Drill mounted jiffy type mixers at 450-500 rpm can also be used. Always add clean potable water first. Mixing duration should last for 3 to 5 minutes to insure proper material dispersion within mix. The plasterer can best judge the required consistency depending on desired thickness, while observing workability and the degree of bonding to the substrate. Care should be taken not to exceed 12 liters of water per 35 kg bag.

APPLICATION • *DashCrete* is best applied by dashing machine or spray plaster machine to a thickness of not less than 2 mm. Insure proper and full coverage of substrate to provide a unified surface absorption for subsequent coats. Once cured, and prior to subsequent coat applications, run a darby or rod over the dry surface to remove loose materials.

CURING • *DashCrete* is designed to be air cured. Under extreme heat condition, cover surface with polyethylene plastic sheeting.

CLEANING • Clean all tools and equipment promptly with clean water.

STORAGE • Keep material covered to prevent exposure to moisture. Store in a dry area. Shelf life is 12 months from date of purchase if stored under recommended conditions in original unopened container.

SAFETY PRECAUTIONS • KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. Portland cement based products present health hazards. Irritating to eyes and skin. Do not breath dust. Use neoprene gloves and a dust mask when handling. FIRST AID: Eyes – Do not rub eyes, immediately flush with fresh water. Skin – Wash with soap and water. Inhalation – If experience difficulty breathing or if inhaled, move to fresh air. If symptoms persist, seek medical attention.

PACKAGING • 35 kg paper bags.

Creative Concrete Concepts

PO Box 925794, Amman 1110, Jordan; Tel +962-6-487-4078, Fax +962-6-488-9133 • PO Box 91234, City of Industry, CA 91715-1234, USA; Tel +1-909-266-0709, Fax +1-909-266-0711 • PO Box 31017, Sharjah, UAE; Tel +971-6-532-1119, Fax +971-6-532-8833